

# Tekniflex® PCTFE Films available @ Tekni-Plex

VAPOSHIELD™ PCTFE film range	Gauge		MVTR g/m2/day @ 38°C/90% RH	Polymer type	ACLAR® PCTFE film range	Gauge		MVTR g/m2/day @ 38°C/90% RH	Polymer type
	µm	mil				µm	mil		
VAPOSHIELD™ DF0010	10	0.4	0.45	Homopolymer	-	-	-	-	-
-	-	-	-	-	ACLAR® 88A	19	0.75	0.47	copolymer
VAPOSHIELD™ DF0015	15	0.6	0.39	Homopolymer	ACLAR® Rx160	15	0.6	0.39	Homopolymer
VAPOSHIELD™ DF0020	20	0.8	0.29 (1)	Homopolymer	ACLAR® Rx20e	20	0.8	0.29 (1)	Homopolymer
-	-	-	-	-	ACLAR® 22A	38	1.5	0.31	copolymer
VAPOSHIELD™ DF0025	23	0.9	0.23	Homopolymer	ACLAR® SupRx900	23	0.9	0.23	Homopolymer
VAPOSHIELD™ DF0038	38	1.5	0.15	Homopolymer	-	-	-	-	-
-	-	-	-	-	ACLAR® 33C	50	2	0.12	copolymer
VAPOSHIELD™ DF0050	50	2	0.11	Homopolymer	ACLAR® UltRx2000	50	2	0.11	Homopolymer
VAPOSHIELD™ DF0075	76	3	0.07	Homopolymer	ACLAR® UltRx3000	76	3	0.07	Homopolymer

Vaposhield™ is a registered trademark of Tekni-Plex Inc

ACLAR® is a registered tradename of Honeywell International Inc.

(1) MVTR g.m<sup>-2</sup>.day at 38°C/100% RH