

*Thermoformable, FDA-compliant, Pharmaceutical-Grade PCTFE film lamination.
Tekni-Plex offers a wide range of PVC-based film structures to meet both performance and cost requirements.*

Typical Physical Properties**General**

Construction	380 μ PVC / 50 μ PCTFE	15.0 mil PVC / 2.0 mil PCTFE
Color	Clear Tint	Clear Tint
Haze	4%	4%
Specific Gravity	1,41 g / cm ³	1.41 g / cm ³
Total Thickness	432 μ	0.0170"
Thickness tolerance	\pm 10%	\pm 10%
Maximum roll width	1,1 m	42"
Roll width tolerance	\pm 1,5 mm	\pm 1/16"
Yield	1,474-1,802 m ² / kg	1037-1267 in ² / lb

Mechanical

Tensile Strength	41,37 x 10 ⁶ N / m ²	6000 psi
------------------	--	----------

Thermal

Dimensional Stability	\pm 4% (30 minutes @ 140°C)	\pm 4% (30 minutes @ 284°F)
Thermoforming Range	100 – 160°C	212 – 320°F

Barrier

Moisture Vapor Transmission Rate (38°C, 90% RH)	0,11 g / m ² / 24 hrs	0.007 g / 100 in ² / 24 hrs
Oxygen Transmission Rate (23°C, 100% RH)	12,4 cm ³ / m ² / 24 hrs	0.8 cm ³ / 100 in ² / 24 hrs

Manufactured under Industry Accepted standards for cGMP. Film is composed of ingredients in compliance with existing regulations of the FDA (21 C.F.R. 175.300, 177.1520 & 177.1380) and EP (3.1.11) and is entered in Tekni-Plex Inc.'s Drug Master File #1378. Data supplied in good faith for information only. End user assumes all liability in using this product for the purpose intended.

TEKNIFLEX® is a registered trademark of Tekni-Plex, Inc.

25/06/2002

TEKNI-FILMS

Tekni-Films USA
201 Industrial Parkway
Somerville, NJ 08876
USA
Tel : (908) 722-4800
Fax : (908) 722-4967

Tekni-Films Europe
Industrielaan, 37
9320 Erembodegem
Belgium
Tel : +32 53 650711
Fax : +32 53 672074

Tekni-Films South America
Timoteo Gordillo 5490
1439 Buenos Aires
Argentina
Tel : +54 11 46054042
Fax : +54 11 46059625