

*Thermoformable, FDA-compliant, Pharmaceutical-Grade PVC / PVdC film.
Tekni-Plex offers a wide range of PVC-based film structures to meet both performance and cost requirements.*

Typical Physical Properties

General

Construction	250µ PVC / 40 g per m ² PVdC	9.8 mil PVC / 40 g per m ² PVdC
Color	White	White
Haze	5%	5%
Specific Gravity	1,41 g / cm ³	1.41 g / cm ³
Total Thickness	273µ	0.0107"
Thickness tolerance	± 7%	± 7%
Maximum roll width	1,3 m	51"
Roll width tolerance	± 1 mm	± 1/25"
Nominal Yield	2,597 m ² / kg	1826 in ² / lb

Mechanical

Tensile Strength	37,92 x 10 ⁶ N / m ²	5500 psi
------------------	--------------------------------------------	----------

Thermal

Dimensional Stability	± 4% (30 minutes @ 140°C)	± 4% (30 minutes @ 284°F)
Thermoforming Range	100 – 160°C	212 – 320°F

Barrier

Moisture Vapor Transmission Rate (38°C, 90% RH)	0,65 g / m ² / 24 hrs	0.042 g / 100 in ² / 24 hrs
Oxygen Transmission Rate (23°C, 50% RH)	0,65 cm ³ / m ² / 24 hrs	0.042 cm ³ / 100 in ² / 24 hrs

Manufactured under Industry Accepted standards for cGMP. Film is entered in Tekni-Plex Inc.'s Drug Master File #1378. Data supplied in good faith for information only. End user assumes all liability in using this product for the purpose intended.

TEKNIFLEX® is a registered trademark of Tekni-Plex, Inc.

25/06/2002

TEKNI-FILMS

Tekni-Films USA
201 Industrial Parkway
Somerville, NJ 08876
USA
Tel : (908) 722-4800
Fax : (908) 722-4967

Tekni-Films Europe
Industrielaan, 37
9320 Erembodegem
Belgium
Tel : +32 53 650711
Fax : +32 53 672074

Tekni-Films South America
Timoteo Gordillo 5490
1439 Buenos Aires
Argentina
Tel : +54 11 46054042
Fax : +54 11 46059625