

*Thermoformable, FDA-compliant, Pharmaceutical-Grade PVC / PVdC film.  
Tekni-Plex offers a wide range of PVC-based film structures to meet both performance and cost requirements.*

## Typical Physical Properties

<b>General</b>		
Construction	300µ PVC / 40 g per m <sup>2</sup> PVdC	11.8 mil PVC / 40 g per m <sup>2</sup> PVdC
Color	Clear Tint	Clear Tint
Haze	5%	5%
Specific Gravity	1,39 g / cm <sup>3</sup>	1.39 g / cm <sup>3</sup>
Total Thickness	323µ	0.0127"
Thickness tolerance	± 7%	± 7%
Maximum roll width	1,3 m	51"
Roll width tolerance	± 1 mm	± 1/25"
Nominal Yield	2,220 m <sup>2</sup> / kg	1561 in <sup>2</sup> / lb
<b>Mechanical</b>		
Tensile Strength	41,36 x 10 <sup>6</sup> N / m <sup>2</sup>	6000 psi
<b>Thermal</b>		
Dimensional Stability	± 4% (30 minutes @ 140°C)	± 4% (30 minutes @ 284°F)
Thermoforming Range	100 – 160°C	212 – 320°F
<b>Barrier</b>		
Moisture Vapor Transmission Rate (38°C, 90% RH)	0,60 g / m <sup>2</sup> / 24 hrs	0.039 g / 100 in <sup>2</sup> / 24 hrs
Oxygen Transmission Rate (23°C, 50% RH)	0,65 cm <sup>3</sup> / m <sup>2</sup> / 24 hrs	0.042 cm <sup>3</sup> / 100 in <sup>2</sup> / 24 hrs

*Manufactured under Industry Accepted standards for cGMP. Film is composed of ingredients in compliance with existing regulations of the FDA (21 C.F.R. 175.300) and is entered in Tekni-Plex Inc.'s Drug Master File #1378. Data supplied in good faith for information only. End user assumes all liability in using this product for the purpose intended.*

TEKNIFLEX® is a registered trademark of Tekni-Plex, Inc.

25/06/2002

## TEKNI-FILMS

Tekni-Films USA  
201 Industrial Parkway  
Somerville, NJ 08876  
USA  
Tel : (908) 722-4800  
Fax : (908) 722-4967

Tekni-Films Europe  
Industrielaan, 37  
9320 Erembodegem  
Belgium  
Tel : +32 53 650711  
Fax : +32 53 672074

Tekni-Films South America  
Timoteo Gordillo 5490  
1439 Buenos Aires  
Argentina  
Tel : +54 11 46054042  
Fax : +54 11 46059625