



Patent Pending

*Thermoformable, FDA-compliant, Pharmaceutical-Grade PCTFE film lamination. Tekni-Plex offers a wide range of PVC-based film structures to meet both performance and cost requirements.*

### Typical Physical Properties

General		
Construction	125µ PVC / 20µ PCTFE / 125µ PVC	5.0 mil PVC / 0.8 mil PCTFE / 5.0 mil PVC
Color	Clear Tint	Clear Tint
Haze	3 %	3 %
Specific Gravity	1,38g / cm <sup>3</sup>	1.38g / cm <sup>3</sup>
Total Thickness	270µ	0.0108"
Thickness tolerance	± 10%	± 10%
Maximum roll width	1,1 m	42"
Roll width tolerance	± 1,5 mm	± 1/16"
Yield	2.376 – 2.904 m <sup>2</sup> / kg	1669 – 2039 in <sup>2</sup> / lb
Mechanical		
Tensile Strength	37.92 x 10 <sup>6</sup> N / m <sup>2</sup>	5500 psi
Thermal		
Dimensional Stability	± 4% (30 minutes @ 140°C)	± 4% (30 minutes @ 284°F)
Thermoforming Range	100 – 160°C	212 – 320°F
Barrier		
Moisture Vapor Transmission Rate (38°C, 90% RH)	0,27 g / m <sup>2</sup> / 24 hrs	0.017 g / 100 in <sup>2</sup> / 24 hrs
Oxygen Transmission Rate (23°C, 100% RH)	18.6 cm <sup>3</sup> / m <sup>2</sup> / 24 hrs	1.2 cm <sup>3</sup> / 100 in <sup>2</sup> / 24 hrs

**Storage Conditions and Shelf-life :** it is recommended to store the reels in original packaging between 18°C-25°C and 40%-60% RH. The component shelf-life is 2 years after date of manufacture on label. Manufactured under Industry Accepted standards for cGMP. Film is composed of ingredients in compliance with existing regulations of the FDA , USP and is entered in Tekni-Plex Inc.'s Drug Master File #1378. Data supplied in good faith for information only. End user assumes all liability in using this product for the purpose intended. It is the customer's responsibility to inspect and test this product as to the suitability for the customer's particular purpose, including but not limited to the use in conjunction with other materials or products; and/or the processing or transformation of this product. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product.

TEKNIFLEX® is a registered trademark of Tekni-Plex, Inc.

MvB 11-Jul-2007

#### TEKNI-FILMS

Tekni-Films USA  
201 Industrial Parkway  
Somerville, NJ 08876 USA  
Tel : (908) 722-4800 - Fax : (908) 722-4967

Tekni-Films Europe  
Industrielaan, 37  
9320 Erembodegem Belgium  
Tel : +32 53 650711 - Fax : +32 53 672074

Tekni-Films South America  
Timoteo Gordillo 5490  
1439 Buenos Aires Argentina  
Tel : +54 11 46054042 - Fax : +54 11 46059625