



TECHNICAL DATA SHEET
PRODUCT TEKNILID 1250

Material: Aluminum Lidding Foil, 20 micron Hard Temper for applications requiring a “push through” feature.

General Description: Overlacquer/ Aluminum/ Heatseal-lacquer based on PVC, PVDC.

TECHNICAL CHARACTERISTICS:

	Unit of measurement	Medium value
Total weight	g/m ²	62.2
Weight of primer for printing	g/m ²	1.2
Weight of aluminum	g/m ²	54.0
Weight of the thermosealable varnish	g/m ²	7.0
Bonding against PVC	N/15mm	min. 6.0
Bonding against PVDC	N/15mm	min. 6.0
Resistance of the primer for printing to the temperature	°C	max. 220
Melting point of the thermosealable varnish	°C	100
Ultimate tensile stress of aluminum	MPa	> 150
Elongation to aluminum breaking	%	> 1.5
Yield:	16.1 m ² /kg Or	11,318 in ² /lb

STORAGE CONDITIONS:

The recommended conditions of storage are: Temperature between 18°C - 30°C (optimum 18°C - 20°C) - Relative humidity between 40% and 60% (optimum 40% - 50%) - Time of storage: 12 months maximum.

Property data represented above are typical and are not specifications.

The information supplied on this Tech-Data Sheet is believed to be accurate but is based on laboratory tests which do not simulate actual use conditions. NO REPRESENTATION, GUARANTEE OR WARRANTIES OF ANY KIND ARE MADE AND TEKNI-PLEX INC. SPECIFICALLY DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Tekni-Plex inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Tekni-Plex’s direct control. Regardless of recommendations made, all uses of lining material should be tested and verified for suitability in the specific intended application.